

Polypropylene Random Copolymer

For High Clarity Injection Molding

Product Description

Topilene® R1101 is a specially designed polypropylene random copolymer that features excellent transparency and high flowability. It is suitable for food containers, transparent containers, housewares, stationery, TWIM parts and big size articles. **Topilene® R1101** is phthalate-free product.

Characteristics

Typical Application Food containers / Transparent container / Housewares / Stationery / TWIM(Thin Wall

Injection Molding) parts / Big size articles

Features High transparency / Excellent flowability & Processability / Phthalate-Free / Non Peroxide

Cracking / Excellent stiffness and impact strength balance

Typical Properties

Resin Properties	Method	Value	Unit
Melt Index(230°C, 2.16kg)	ASTM D1238	85	g/10min
Density	ASTM D792	0.90	g/cm³
Tensile Strength at Yield	ASTM D638	300	kg/cm²
Flexural Modulus	ASTM D790	11,000	kg/cm²
Notched Izod Impact Strength(23°C)	ASTM D256	4.5	kg·cm/cm
Rockwell Hardness	ASTM D785	85	R-Scale
Haze(2mm)	ISO 14782	20	%

The values listed above are typical values for reference purpose only and shall not be construed as specifications. *Topilene*® is a registered trademark owned or used by HYOSUNG CHEMICAL CORPORATION.

Energy Savings

Topilene® R1101 provides improved aesthetics at significantly lower process temperatures that leads to lowered energy consumptions, shortened cycle time and improved productivity. It enables an average of 10% energy savings for production of clarified PP parts.

Storage and Handling

This product should be stored in dry condition at temperature below 40° C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: $80\sim100^{\circ}$ C/2~4hours at air circulated condition)





Contacts

Head Office 235, Banpo-daero, Seocho-gu, Seoul, Korea 06578

Tel: +82-2-2146-5451~7 Fax: +82-2-2146-5428

Online www.hyosungchemical.com

www.topilene.com





