

## Polypropylene Random Copolymer

For High Clarity Injection Molding

### **Product Description**

**Topilene® R801** is a specially designed polypropylene random copolymer that features excellent transparency and high flowability. It is suitable for food containers, medical syringes, transparent containers, housewares, stationery, TWIM parts and big size articles. **Topilene® R801** is phthalate-free and it complies with FDA requirements in the code of Federal Regulations in 21 CFR 177.1520 for food contact.

#### **Characteristics**

Typical Application Food containers / Transparent container / Housewares / Medical syringes / Stationery /

TWIM(Thin Wall Injection Molding) parts / Big size articles

Features High transparency / Excellent flowability & Processability / Phthalate-Free / Non Peroxide

Cracking / Excellent stiffness and impact strength balance

## **Typical Properties**

Resin Properties	Method	Value	Unit
Melt Index(230°C, 2.16kg)	ASTM D1238	30	g/10min
Density	ASTM D792	0.90	g/cm³
Tensile Strength at Yield	ASTM D638	300	kg/m²
Flexural Modulus	ASTM D790	11,000	kg/cm²
Notched Izod Impact Strength(23°C)	ASTM D256	6.0	kg·cm/cm
Rockwell Hardness	ASTM D785	90	R-Scale
Heat Deflection Temperature	ASTM D648	90	°C
Haze(2mm)	ISO 14782	20	%

The values listed above are typical values for reference purpose only and shall not be construed as specifications. *Topilene*<sup>®</sup> is a registered trademark owned or used by HYOSUNG CORPORATION.

## **Energy Savings**

**Topilene® R801** provides improved aesthetics at significantly lower process temperatures that leads to lowered energy consumptions, shortened cycle time and improved productivity. It enables an average of 10% energy savings for production of clarified PP parts.

# Storage and Handling

This product should be stored in dry condition at temperature below  $40^{\circ}$ C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition:  $80\sim100^{\circ}$ C/2~4hours at air circulated condition)





#### **Contacts**

**Head Office** 235, Banpo-daero, Seocho-gu, Seoul, Korea 06578

Tel: +82-2-2146-5451~7 Fax: +82-2-2146-5428

Online www.hyosungchemical.com

www.topilene.com





